





SAYREVILLE STEEL MILL  
NORTH CROSSMAN ROAD  
SAYREVILLE NJ 08872 USA  
(732) 721-8600

Chemical and Physical Test Report

MADE IN UNITED STATES

S-085939

PRODUCED IN: SAYREVILLE

SHIP TO  
PICKETT BLD  
6469 STATE HWY 23  
607-432-8391  
ONEONTA, NY 13820

INVOICE TO  
BLUELIX CORP/ANE  
GENERAL ACCOUNT  
ATTN: ACCTS PAYABLE DIST. DIV  
ATLANTA, GA 30339-8401

SHIP DATE  
01/04/08  
CUST. ACCOUNT NO  
60157146

SHAPE # SIZE	GRADE	SPECIFICATION	SALES ORDER	CUST.P.O. NUMBER
X16MM REBAR (# 5)	420 (60)	ASTM A615M GR420 (GR60)	7131073-02	ANE92967D-02
HEAT I.D.	G	S	C	Eqv
S800028	.47	.046	.000	.627
	P	.009	.000	.000
	Mn	.86	.000	.000
	Si	.20	.000	.000
	Cu	.27	.000	.000
	Ni	.08	.000	.000
	Cr	.07	.000	.000
	Mo	.033	.000	.000
	V	.001	.000	.000
	Nb	.005	.000	.000
	B	.000	.000	.000
	N	.000	.000	.000
	Sn	.017	.000	.000
	Al	.000	.000	.000
	Ti	.000	.000	.000
	Zr	.000	.000	.000
	Ca	.000	.000	.000

Mechanical Test: Yield 64926 PSI, 447.65 MPA Tensile: 104378 PSI, 719.23 MPA %El: 11.08in, 11.07200MM Bend: OK Def: 0, 0MM %Wh 0L  
Mechanical Test: Yield 63455 PSI, 437.51 MPA Tensile: 103670 PSI, 714.37 MPA %El: 11.08in, 11.07200MM Bend: OK Def: 0, 0MM %Wh 0L

This material, including the bills, was produced and manufactured in the United States of America

*Shastrow*  
Bhaskar Valamanchilli  
Quality Director  
Gerdau Ameristeel

*Julius J. Bergend*  
Mgr. Metallurg. Svcs.  
SAYREVILLE STEEL MILL

THE ABOVE FIGURES ARE CERTIFIED EXTRACTS FROM THE ORIGINAL CHEMICAL AND PHYSICAL TEST RECORDS AS CONTAINED IN THE PERMANENT RECORDS OF COMPANY

Seller warrants that all material furnished shall comply with specifications subject to standard published manufacturing variations. NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, ARE MADE BY THE SELLER, AND SPECIFICALLY EXCLUDED ARE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. In no event shall seller be liable for indirect, consequential or punitive damages arising out of or related to the materials furnished by seller. Any claims for damages for materials that do not conform to specifications must be made from buyer to seller immediately after delivery of same in order to allow the seller the opportunity to inspect the material in question.