




Construction Geosynthetics

RETAINING WALL



SG 150

STRATAGRID geogrids are constructed of high molecular weight and high tenacity polyester yarns utilizing a complex knitting process and polymer coating to provide superior engineering properties. STRATAGRID is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in aggressive soil environments (pH range from 3-9).

Property	Test Method	English	Metric
Ultimate Strength	ASTM D-6637 Method A	1,875 lbs/ft	27.4 kN/m
Creep Reduction Factor		1.65	1.65
Long Term Design Strength (Sands, Silt and Clay)	LTDS or Tal	861 lbs/ft	12.6 kN/m
Creep Limited Strength		1,136 lbs/ft	16.6 kN/m
Molecular Weight (min.)	GRI GG8	25,000 g/mol	25,000 g/mol
Carboxyl End Group Count (max.)	GRI GG7	30 Meg/kg	30 Meg/kg
Aperture Size	Measured	.95 x .90 in	24.1 x 22.9 mm

Roll Size	Roll Diameter	Area	Weight
6' x 150'	9.0 in	100 sys	45 lbs
12' x 150'	11.0 in	200 sys	90 lbs

This information is provided for reference only and is not intended as a warranty or guarantee. US Fabrics assumes no liability in connection with the use of this information (1/2018).

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227

Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: info@usfabrics.com